

Intrada SEC


250 x 4.6 mm

Application

Polyacrylate


ポリアクリル酸

Na



sodium polyacrylate

$n = 30,000 - 40,000$



*Intrada SEC, 250 x 4.6 mm
 100mM ammonium formate
 0.3 mL/min (5MPa), 37°C
 10 µL, (1mg/mL, 100mM HCOONH4)
 ELSD (Spray Chamber 50°C, Drift Tube 100°C)*