Intrada *SEC* 250 x 4.6 mm Application

SEC: Poly-gamma-glutamic acid

ポリ-γ-グルタミン酸のSEC分離



poly-gamma-glutamic acid (MW 1.5 - 2.5 MDa, Na salt)



Intrada SEC, 250 x 4.6 mm
100mM ammonium formate
0.3 mL/min (5MPa), 37°C
5 µL (1mg/mL, eluent)